

Bureau of Research, Testing and Consultation (BRTC)
 To check authenticity of this report, please scan the QR Code.
 Alternatively, please visit <http://brtc.mme.buet.ac.bd>.

Department of Materials and Metallurgical Engineering (MME)
 Bangladesh University of Engineering and Technology (BUET)

Client: Mr. Md. Golam Mowla
 QC Manager
 Shahriar Steel Mills Limited
 Konapara, Jatrabari
 Dhaka 1362

Client's Reference: Nil; Date 04/03/2020
 BRTC Reference: 1102-09488/MME/2019-20; Date 04/03/2020
 Sample Condition: Not Sealed

Date: 09 March 2020
 MME No: 0956(01)/2019-20

TEST OF DEFORMED M.S. REBAR

Frog Mark/ Description	Sample No.	Bar	Actual Dia	Unit Weight	Average Unit Weight	Yield Load	Yield Strength	Average Yield Strength	Tensile Load	Tensile Strength	Average Tensile Strength	TS/YS Ratio	Elongation (G.L. 200 mm)	Average Elongation	Bend Test (Separate Samples)
		Designation / Nominal Dia													
SSRM RB 400 10	1	10	9.83	0.595	0.594	33.55	427	428	49.56	631	635	1.48	14	15	Satisfactory
	2	10	9.79	0.592	0.594	33.07	421	428	49.65	632	635	1.50	15	15	Satisfactory
	3	10	9.84	0.596	0.594	33.07	421	428	49.65	632	635	1.50	15	15	Satisfactory

*TS/YS ratio is not required as per ASTM A615M.
 *Strength values are calculated based on nominal area.

Weight Requirements for Steel Rebar (As Per ASTM A615/A615M—16 Table A1.1)

Bar Designation Number/Nominal Dia., mm	10	12	16	20	25	28	32	36	40	50	60
Nominal Weight, kg/m	0.617	0.888	1.578	2.466	3.853	4.834	6.313	7.990	9.865	15.410	22.200

* Measured unit weight shall not be less than 94% of the nominal weight.

Minimum Tensile Requirements for Steel Rebar (As Per ASTM A615/A615M—16 Table A1.2)

Grade	Yield Strength	Tensile Strength	ASTM A615M		Minimum Elongation in 8 in. (200 mm) Gauge Length, per cent	
			Grade	Yield Strength	Tensile Strength	Bar Designation Number
40	40,000 (280)	60,000 (420)	280	280 (40,000)	420 (60,000)	10, 12, 16, 20, 25, 28, 32, 36, 40, 50, 60
60	60,000 (420)	90,000 (630)	420	420 (60,000)	620 (90,000)	10, 12, 16, 20, 25, 28, 32, 36, 40, 50, 60
75	75,000 (520)	100,000 (690)	520	520 (75,000)	690 (100,000)	10, 12, 16, 20, 25, 28, 32, 36, 40, 50, 60
80	80,000 (550)	105,000 (725)	550	550 (80,000)	725 (105,000)	10, 12, 16, 20, 25, 28, 32, 36, 40, 50, 60
100	100,000 (690)	115,000 (790)	690	690 (100,000)	790 (115,000)	10, 12, 16, 20, 25, 28, 32, 36, 40, 50, 60

Dr. Fahmida Gulshan
 Professor and Head
 44x0ue0tn
 09.03.2020



Please note: The client supplied the sample(s) and the result given herewith corresponds to the sample(s) tested only. Department of MME, BUET takes no responsibility regarding the misidentification, if any, of the sample(s).